



CorShield® Gold



PRODUCT DESCRIPTION

CorShield Gold is a brilliant true gold colored waterbased coating. It has excellent salt spray and humidity resistance similar to VpCI®-386 Aluminum and is available in one package system. CorShield Gold provides protection in harsh, outdoor, unsheltered applications. The complex mixture of non-toxic organic inhibitors and a platelet type gold pigment offers protection that can compete with zinc rich coatings. This special combination of additives, a platelet pigment, and a polymer barrier, significantly retards the reaction of metal ionization and repels water. It protects against corrosive electrolytes and aggressive environments, thus preventing corrosion.

CorShield Gold provides a fast-drying thixotropic coating that is resistant to sagging, forming a tough, non-flammable, protective barrier. This dry-to-touch film offers extended protection for sheltered or unsheltered, outdoor or indoor conditions. Thermally stable from -40°F to 400°F (-40°C to 204°C), the coating is ultraviolet resistant. It gives optimal out-

door performance without cracking or chipping upon prolonged exposure to sunlight.

CorShield Gold has exceptionally good anti-abrasion qualities, making it easily adaptable for steel grating walkways and decks. The gold color is ideally suited for use on motorcycles, ATVs, sporting goods, lamp fixtures, and olympic events.

FEATURES

- Brilliant gold color
- Fast-drying
- UV resistant
- Optimal outdoor performance
- Excellent corrosion resistance
- Waterbased

APPLICATIONS

CorShield Gold can be used as a single coat for most applications. For extreme exposures it can also be used as a topcoat with Cortec VpCI-374 or VpCI-395 as a primer.

Note: Make certain that the dew point is more than 5°F (2°C) less than air temperature for application and the temperature is at least 55°F (13°C) for best results in the field applications.

METALS PROTECTED

- Carbon steel
- Cast iron
- Aluminum
- Stainless steel
- Galvanized steel
- Copper



TYPICAL PROPERTIES

Appearance	Gold liquid
pH	9.0-9.6 (Neat)
Density	8.4-8.9 lb/Gal. (1.01-1.07 Kg/l)
Non-volatile Content	35 to 42%
Dry Film Thickness	1.5-2.5 mils 37.5-62.5 microns
Dry to touch time	30 min at 75°F (24°C)
VOC	1.3 lb/gal (152 g/liter)
Viscosity	700-1400cps (6 rpm/#3 spindle)
Coverage at 2mils (50 microns)	320 ft ² /gal (7.9m ² /l)

PACKAGING AND STORAGE

CorShield Gold is available in 5 gallon (19 liter) pails and 55 gallon (208 liter) drums, and liquid totes. Keep product from freezing. Mix before use.

TEST DATA (VpCI-386 FR Top Coat)

Test Method	SAE 1010 Carbon Steel	Aluminum
Salt Spray (ASTM B-117)	300-500 hours*	1000+hours
Humidity(ASTM D-1748)	1000+hours	1000+hours

*1.5 to 2.0 mils (37.5 to 50 microns)

Conventional Spray

Manufacturers	Gun Model	Tip/Aircap Combination
DeVibiss	MBC or JGA	704E
Binks	#18 or #62	66PE

Fluid hose should be 3/8" (0.95 cm) I.D. with a maximum length of 50 feet (15.2 m). Pot should always have dual regulation and be kept at some elevation as spray gun.

Airless

Manufacturing	Gun Model	Tip/Aircap Combination
Graco	205-91	Bulldog
Binks	Model 500	Mercury 5C
DeVibiss	Jgn-501	QFA-519

Hose should be 3/8" (0.95 cm) I.D. minimum, but a 1/4" (0.64 cm) I.D. ship end section may be used for ease of application. A maximum length of 100 feet (30.5 m) is suggested. Best results will be obtained using a 0.013"-0.017" (0.3-0.4 cm) tip at 1200-1700 psi (83-117 bar).

Note: Nylon or Teflon type packagings are available from pump manufacturer and are highly recommended. Similar equipment may be suitable.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet http://www.cortecvci.com

printed on recycled paper  100% post consumer

Revised 6/30/11. ©Cortec Corporation 2002-2011. Supersedes: 03/11/02.
© 2011, Cortec Corporation. Cortec, CorShield, and VpCI are trademarks of Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.

Distributed by: